



FILAMENT DATASHEET

MATERIAL: Architectural Line - Monumental, Heritage Brick, Clay, Sandy, Caementum, Darkstone

WE CARE ABOUT YOUR PRINTS

Suggested printing specs.	Value	Unit	Standard
Extruder Temperature	230° +/-10°	°C	Internal
Bed Temperature	100° +/-10°	°C	Internal
Print speed	60-70	mm/s	Internal
Fan	0-20	%	Internal
Minimum Nozzle Diameter	0,35	mm	Internal
Material Properties			
Water Absorption	0,2	%	ISO 179
Tensile Modulus	2500	Pa	ISO 527
Vicat Softening Temperature	102°	°C	ISO 96
Charpy Impact at 23°C	8	ft·lb/in ²	ISO 179
Charpy Impact at -30°C	3	ft·lb/in ²	ISO 179
MFR	4	g/10 min	ISO 1133

DISCLAIMER

The Information presented herein has been compiled from sources considered to be dependable and is accurate to the best of our knowledge. However, since data, safety standards, and government regulations are subject to change and the conditions of handling and use, or misuse, are beyond our control, Sa2p/Treed Filaments makes no warranty expressed or implied, with respect to completeness or continuing accuracy of the information contained herein and disclaims all liability for reliance thereon.

User should satisfy himself that he has all current data relevant to his particular use.